



## Processing set for FOMAPAN R100

### Efficiency of the set

- for processing of 8 pcs 135/36 FOMAPAN R 100 cine-films  
(or 2 pcs 2x8 mm/10.5 m; 1 pc 16 mm/30 m).
- for preparation of 8x330 ml of processing baths.

### Content of the set:

1st and 2nd developer	Identification	<b>A</b>	= 1 pc of concentrate in PE bottle 250 ml
Bleaching bath	Identification	<b>B<sub>1</sub></b>	= 1 pc of concentrate in PE bottle 250 ml
		<b>+B<sub>2</sub></b>	= 1 pc of concentrate in PE bottle 250 ml
			<b>Prepare processing bath immediately before using.</b>
Cleaning bath	Identification	<b>C</b>	= 1 pc of concentrate in PE bottle 250 ml
Fixing bath	Identification	<b>D</b>	= 1 pc of concentrate in PE bottle 500 ml

### Preparation of baths to process 1 pc of 135/36 cine-film:

- A** 300 ml of water + 30 ml of **A** solution
- B** 300 ml of water + 30 ml of **B<sub>1</sub>** solution + 30 ml of **B<sub>2</sub>** solution
- C** 300 ml of water + 30 ml of **C** solution
- D** 300 ml of water + 60 ml of **D** solution

It is recommended to use distilled or boiled water to prepare baths. Prepare processing bath immediately before using. Do not store solved (thinned) solutions! Have an authorised organisation to dispose of used solutions.

### Procedure of processing:

- 1) Developer **A** 12 min / 20 °C ±0.5 °C
- 1a) Rinsing with running water 2 min / 20 °C ± 5 °C
- 2) Bleaching bath **B** 8 min / 20 °C ± 0.5 °C
- 2a) Rinsing with running water 2 min / 20 °C ± 5 °C
- 3) Cleaning bath **C** 3 min / 20 °C ± 3 °C
- 3a) Rinsing with running water 2 min / 20 °C ± 5 °C
- 4) Re-exposure 2x30 sec.
- 5) Developer **A** (solution used in the 1st developing) 5 min / 20 °C ±0.5 °C
- 5a) Rinsing with running water 2 min / 20 °C ± 5 °C
- 6) Fixing bath **D** 4 min / 20 °C ± 3 °C
- 6a) Rinsing with running water 10 min / 20 °C ± 5 °C
- 6b) Rinsing in distilled water

**Processing** in developing tank with regular slow motion during all processing stages, including rinsing!

### Illumination during processing (stages 1 to 2a) - total dark or infrared lighting.

**Re-exposure** to be done in the developing tank using a 100 W bulb in a distance of 1 m in water and with the film moving (turning the spiral with the film) - 30 sec. from both sides.

End users may drain **used working solutions** to sewage system after thorough thinning (at least 30 more parts of water).